



Clariana

*Buenos papeles hechos
por Buena gente
Good papers made by Good people*

COMMERCIAL SPECIFICATION

QUALITY:

Color Plus Print

Physical Proprieties	Unity	Average	Maximum	Minimum	Norm
Substance	gr./m ²		As Order \pm 4 %		UNE-57014-74
Whiteness Elrepho 2000	%	---	---	---	UNE-57062-72
Smoothness Bendtsen (Inside)	ml/min.	130	255	100	UNE-57080-88
Smoothness Bendtsen (Outside)	ml/min.	135	315	100	UNE-57080-88
Porosity Bendtsen	ml/min.	1000	1500	600	UNE-57066-86/2
Sizing Cobb 60" (Inside)	gr. H ₂ O	30	35	25	UNE-57027-74
Sizing Cobb 60" (Outside)	gr. H ₂ O	30	35	25	UNE-57027-74
Bulk	cm ³ /gr	1,30	1,35	1,25	UNE-EN 20534
Thickness	μ	Calculate Bulk * Substance			UNE-57004-88
Moisture	%	4,7	5,0	4,5	UNE-57005-90
Tensile Strength (M.D.)	m	6000	8000	5000	UNE-57028-74
Tensile Strength (C.D.)	m	3500	5000	3000	UNE-57028-74

Quality Management	General Management
<i>Miguel Goenaga</i>	<i>Rubén Simarro</i>